

# Creation 55



gerflor.com / follow us



20014019

## DESCRIPTION / BESCHREIBUNG / DESCRIPCIÓN / DESCRIPCIÓN / DESCRIÇÃO / DESCRIZIONE

Description / Beschreibung / Descripción / Descripción / Descrição / Descrizione	Creation 55 Trend		Creation 55 Design		Creation 55 Solid Clic	Creation 55 Rigid Acoustic	Creation 55 Looseley Acoustic
	EN ISO 24346	mm	EN ISO 24346	mm			
Total Thickness / Gesamtstärke / Totale dikte / Épaisseur totale / Espesor total / Espessura total / Spessore totale	2.50	4.00	4.00	4.50	4.50	5.50	5.50
Thickness of the wearlayer / Dicke der Nutzschicht / Dikte van de slijdlag / Épaisseur couche d'usure / Espesor capa de uso / Espessura camada de desgaste / Spessore strato d'usura	0.10	0.20	0.24	0.18	0.20	0.20	0.20
Weight / Flächengewicht / Gewicht / Poids / Peso / Peso	0.35	0.35	0.35	0.35	0.35	0.35	0.35
Size / Format / Aformaten / Formati / Dimensões / Dimensões / Dimensione	0.022	0.02	0.022	0.022	0.02	0.02	0.02
Number of planks / m²	3.950	4.410	4.480	7.500	7.500	7.600	7.600
Number of planks or tiles per box / Stm per box - Planken- / Fliesenanzahl pro Kasten / Numero di piastrelle per confezione / aantal m² per verpakking - Nombre de jantes ou dalles par boîte / m² per caixa - Numero doboi/parastre m² per scatola - Cantidad de losetas / Caja / Quantidade dosmosaicos / Caixa & m²	4572x914,4mm/18"x36"/19,326m² 605x609,6mm/24"x24"/19,336m² 184,15x1219,2mm/2,07x4,87/15,036m² 914x914,4mm/36"x36"/51,418m² 152x762mm/6"x30"/133,336m² 2300x1500,0mm/19'x49'/1913,11m²	212x1228,8/8,37x48,87/17,186m² 177x1219,17x48,87/18,173m² 229,6x1468,8/9,15x16,121m² 388,8x728,7/15,3x28,7/61,10m² 125x760/5"x30"/14,150m² 177x1219,17x48,87/18,173m² 229,6x1468,8/9,15x16,121m² 388,8x728,7/15,3x28,7/61,10m² 457x914,18"x36"/14,150m²	229x1229/9"x48"/18,1723m² 500x500/19"x19"/8,121m² 600x600/24,02x24,02/10,720m²				

## CLASSIFICATION / KLASSIFIKATION / CLASSIFICAZIONE / CLASSIFICAZIONE / CLASSIFICAZIONE / CLASSIFICAZIONE

Norm/Product Specification / Produktnorm / Technische Eigenschaften / Norme / Specificazione prodotti / Normas / Normas / Norma prodotto	EN ISO 10582	EN ISO 10582	EN ISO 10582	EN ISO 10582
European Classification / Europäische Klassifizierung / European classification / Classement européen / Classificação europea / Classificação Europeia / Europa	Class III Type B	Class III Type B	Class III Type B	Class III Type B
Fire Rating / Brandverhalten / Brand classifacatie / Classement Feu / Fuego / Fogo / Reazione al fuoco	33-42	33-42	33-42	33-42
Static Electrical Propensity / Begleitaufladung / Elektrische Eigenschaften / Potentiel de charge / Comportamento electrostático / Comportamento electrostático / Resistencia eléctrica	BlI-s1	BlI-s1	BlI-s1	BlI-s1
Slip Resistance Wet / Rutschhemmung / Anti-slip / Glissance humide / Deslizamiento húmedo / Escorregamento húmido / Scivolosità umida**	<2	<2	<2	<2

## PERFORMANCES / TECHNISCHE EIGENSCHAFTEN / TEST RESULTAAT / PERFORMANCE / CUALIDADES TÉCNICAS / PERFORMANCES / CARATTERISTICHE TECNICHE

Wear Resistance / Verschleißverhalten / Slijtheitheid / Resistencia à Lusura / Abrasion / Resistencia à abrasão / Resistencia all'abrasione	EN 6602	mm²	<2.0	<2.0	<2.0	<2.0
Wear Group / Verschleißgruppe / Groep slijtheiheid / Groupe d'abrasion / Gruppo di abrasão / Gruppo di abrasione	T	group	T	T	T	T
Type Binder content / Bindemittelgehalt / Teneur en agent liant / Conteúdo em ligante / Contenido en agente	I	group	I	I	I	I
Dimensional stability (average measured value) / Maßhaltigkeit (Durchschnittswert) / Stabilità dimensionale (valore promedio mesurado) / Maatvotheid (gemeten gemiddelde waarde) / Estabilidad Dimensional (Valor medio) / Estabilidade Dimensional (Valor médio) / Stabilität dimensionale (fretavet)	€ 0.25	%	€ 0.15	€ 0.15	€ 0.15	€ 0.15
Dimensional stability (average measured value) / Maßhaltigkeit (Durchschnittswert) / Stabilità dimensionale (valore promedio mesurado) / Maatvotheid (gemeten gemiddelde waarde) / Estabilidad Dimensional (Valor medio) / Estabilidade Dimensional (Valor médio) / Stabilität dimensionale (fretavet)	€ 0.10	%	~0.05	~0.05	~0.05	~0.05
Residual indentation / Residualruck / Inruksbelasting / Poinçonnement résiduel émanent / Puncionamento / Imponnia	€ 0.10	mm	€ 0.10	€ 0.05	€ 0.05	€ 0.20
Impact sound insulation / Trittschallverbesserungswert / Isolamento acústico / Redução do ruído acústico	EN ISO 717-2	dB	4	19	7	19
Room Impact / Raumschall / Looppulid / Sonorité à la marche / Rumor al Calpesto / Sonoridade en la pisada / Sonoridade ao andar	NF S 31074	dB	77	81	73	70
Customer chair test / Stuhlrollenbeanspruchung / Rollweerstand bureausstoelen / Essai de la chaise à roulettes / Determinación del efecto de una silla con ruedas / Resistência a cadeiras de rodas / Resistência al passaggio di sed	ISO 4918	-	OK	OK	OK	OK
Thermal Conductivity / Wärmeleitfähigkeit / Thermische weerstand / Conductivité thermique / Conduktividad térmica / Conduvidade térmica / Resistência térmica / Värmeledningsförmåga / Vermenstand	EN ISO 10456	W/(m.K)	0.25	0.25	0.25	0.25
Colour Fastness / Lichtechtheit / Lichtechtheid / Solidité lumière / Resistencia a la luz / Estabilidade das cores / Solidità alla luce	EN ISO 105-B02	Degree	≥6	≥6	≥6	≥6
Surface Treatment / Oberflächevergoldung / Oppervlakbehandeling / Traitement de surface / Tratamiento de superficie / Tratamento de superficie	-	-	ProtectShield®	ProtectShield®	ProtectShield®	ProtectShield®
Chemical Products Resistance / Verhalten gegenüber Chemikalien** / Resistencia a los productos químicos / Resistencia a los productos químicos / Resistencia aos produtos químicos / Resistencia ai prodotti chimici	EN ISO 26987	-	OK	OK	OK	OK

## ENVIRONMENT/INDOOR AIR QUALITY / UMWELT/RAUMLUFTQUALITÄT / AMBIENTE/QUALIDADE DO AR INTERIORENVIRONNEMENT/QUALITE DE L'AIR INTERIEUR / MEDIO AMBIENTE/CALIDAD INTERIOR DEL AIRE INTERIOR / MEIOAMBIENTE/QUALIDADE DO AR INTERIOR

TWOC after 28 days / TWOC (28 days) / TWOC (28 dagen) / TWOC (28 giorni)	ISO 16000-6	µ/m³	<10	<10	<10	<10
Certification / Zeugnis / Certificación / Certificato / Certificação	Floorscore®	Floorscore®	Floorscore®	Floorscore®	Floorscore®	Floorscore®

CE MARKING / CE KENNZEICHNUNG / EG_CONFORMITEITSMERK / MARQUE DE CONFORMIDAD CE / MARCA DE CONFORMIDADE CE / MARCA DE CONFORMIDADE CE / MARCATURA CE DI CONFORMITA	EN 14041	-	EN 14041	-	EN 14041	-

(1) Plan incliné avec bulle / Ramp test with oil / Schiefe Ebene  
 (2) Beadrijg tegenover nicht färbenden alkoholhaltigen Handdesinfektionsmitteln, Haushaltschemikalien und verdünnten Säuren und Laugen bei kurzzeitiger Einwirkung

**we care / we act** Our Commitments for a Sustainable future



**CARBON FOOTPRINT**  
-20 % kg CO<sub>2</sub> equivalent/m<sup>2</sup> between 2020 and 2025



**BIO-SOURCED CONTENT**  
10 % by 2025



**RECYCLED CONTENT**  
30 % by 2025



**ADHESIVE FREE**  
35 % by 2025



**ANNUAL VOLUME RECYCLED**  
60 000 t by 2025



**IMPORTANT:** The information contained in this document is valid from 07/05/2022 and is subject to change at any time without notice. In the context of constantly changing technology, our customers are responsible, prior to any use, for checking with us that this document is the version in force.

\* Scopes 1 and 2 defined in the GHG protocol \*\* % of activity with biosourced materials \*\*\* % of activity - adhesive free solution